

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : C08J 9/28</p>	<p>A2</p>	<p>(11) International Publication Number: WO 95/31500 = EP 767,812 (43) International Publication Date: 23 November 1995 (23.11.95)</p>
<p>(21) International Application Number: PCT/US95/05933 (22) International Filing Date: 12 May 1995 (12.05.95) (30) Priority Data: 242,548 13 May 1994 (13.05.94) US (71) Applicant: UNIVERSITY OF CINCINNATI [US/US]; Mail Location 0829, 201 Wherry Hall, Cincinnati, OH 45267- 0829 (US). (72) Inventors: KABRA, Bhagwati, G.; Apartment 435, 5210 Cameron Creek Circle, Ft. Worth, TX 76132 (US). GEHRKE, Stevin, H.; 5444 Sprucewood Drive, Cincinnati, OH 45239 (US). 4) Agents: MILLER, Martin, J. et al.; Frost & Jacobs, 2500 PNC Center, 201 East Fifth Street, Cincinnati, OH 45202 (US).</p>		<p>(81) Designated States: AU, CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published Without international search report and to be republished upon receipt of that report.</p>

(54) Title: SUPERABSORBENT FOAMS, AND METHOD FOR PRODUCING THE SAME

(57) Abstract

An absorbent, microporous foam comprising a crosslinked polymer having interconnected fluid cells distributed throughout its mass, wherein the fluid cells have a diameter of between about 0.1 and about 100 μm , and wherein the foam can rapidly absorb at least about twice its dry weight in fluid, is disclosed. A method for producing a microporous, absorbent foam is also disclosed. This method comprises the steps of: (a) mixing a cross-linkable polymer and a first solvent to form a stable solution, wherein the stable solution can be induced to phase separate; (b) inducing the stable solution to phase separate into a polymer-concentrated phase and a polymer-dilute phase (after a predetermined period of time; (c) inducing crosslinking of said polymer, so that the polymer will crosslink in said concentrated phase for a predetermined period of time during phase separation to thereby form a microporous material; and (d) drying the microporous material to produce the absorbent foam.

A22



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08J 9/28 // A61L 15/60, A61F 13/15	A3	(11) International Publication Number: WO 95/31500 (43) International Publication Date: 23 November 1995 (23.11.95)
(21) International Application Number: PCT/US95/05933 (22) International Filing Date: 12 May 1995 (12.05.95) (30) Priority Data: 242,548 13 May 1994 (13.05.94) US (71) Applicant: UNIVERSITY OF CINCINNATI [US/US]; Mail Location 0829, 201 Wherry Hall, Cincinnati, OH 45267-0829 (US). (72) Inventors: KABRA, Bhagwati, G.; Apartment 435, 5210 Cameron Creek Circle, Ft. Worth, TX 76132 (US). GEHRKE, Stevin, H.; 5444 Sprucewood Drive, Cincinnati, OH 45239 (US). (74) Agents: MILLER, Martin, J. et al.; Frost & Jacobs, 2500 PNC Center, 201 East Fifth Street, Cincinnati, OH 45202 (US).	(81) Designated States: AU, CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i> (88) Date of publication of the international search report: 4 January 1996 (04.01.96)	
(54) Title: SUPERABSORBENT FOAMS, AND METHOD FOR PRODUCING THE SAME (57) Abstract An absorbent, microporous foam comprising a crosslinked polymer having interconnected fluid cells distributed throughout its mass, wherein the fluid cells have a diameter of between about 0.1 and about 100 μm , and wherein the foam can rapidly absorb at least about twice its dry weight in fluid, is disclosed. A method for producing a microporous, absorbent foam is also disclosed. This method comprises steps of: (a) mixing a cross-linkable polymer and a first solvent to form a stable solution, wherein the stable solution can be induced to phase separate; (b) inducing the stable solution to phase separate into a polymer-concentrated phase and a polymer-dilute phase after a predetermined period of time; (c) inducing crosslinking of said polymer, so that the polymer will crosslink in said concentrated phase for a predetermined period of time during phase separation to thereby form a microporous material; and (d) drying the microporous material to produce the absorbent foam.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

SUPERABSORBENT FOAMS, AND METHOD FOR PRODUCING THE SAME

BACKGROUND OF THE INVENTION

5 Field of the Invention

This invention relates to microcellular, open-celled, superabsorbent polymer foams, and a method for producing the same. The foams thus produced have exceptionally rapid sorption rates, as they absorb and retain liquid by a combination of capillary action and pore wall swelling.

10

Description of Related Art

Microporous, open-celled foams have garnered much interest recently due to their potential for numerous and varied applications. For example, these materials are useful in multishell fusion target experiments, as filtration media, in controlled release systems, and as artificial skin and blood vessels. Microporous, open-celled foams can also be employed in much simpler consumer applications such as reusable diapers and other personal hygiene devices. These latter uses often depend upon the absorbent capabilities of the foam and rate of sorption, as well as its strength.

15

20

Foams can generally be characterized as materials which have numerous fluid-filled cells distributed throughout their mass. The properties of these materials vary greatly, and depend in large part on the degree of interconnectivity of the cells. For example, should it be desired to use the foam as an absorbent, a greater degree of interconnectivity is desired. If the cells in this two phase fluid-

25

solid system are interconnected, the material is termed an "open-celled" foam. Ideally, a foam used for absorbent purposes should have 100% interconnectivity, in which case the material is termed "bicontinuous" or "open-celled." In contrast, closed cell foams have cells which are discrete, having fluid phases which are independent of that of the other cells.

Another characteristic which greatly affects the properties of a foam is the size of its pores. For example, while natural sponge is a well-known absorbent, it cannot be used in products such as diapers because its large, macroscopic pores cannot hold fluids under even the slightest pressure. For a foam to be useful in a diaper, fluid must be retained under a pressure of about ^{3.4 kPa} 0.5 psi. In order to achieve this level of retention, the pores must be microscopic, since only then will the capillary forces responsible for fluid retention be sufficient to withstand applied pressures at the desired levels. In addition, only microscopic pores will retain fluid in competition with other absorbent materials such as clothing ("wicking"). Thus, microporous foams (0.1-100 μm pores) are desired for absorbent purposes.

Conventional, macroporous ($> 100 \mu\text{m}$ pores) polymeric foams can be produced by a number of methods, the most common being a gas dispersion process whereby a gaseous phase is dispersed throughout a liquid polymer phase. The resultant gas-solid state is then preserved either by physical means such as vitrification, or by polymerization and/or crosslinking of the liquid phase. The cell size in these foams, however, is generally 100-200 μm or larger, and thus their usefulness as absorbents is limited. These products do find use as insulation and packaging material.

Microporous (i.e., 0.1-100 μm pores) polymeric foams have generally been produced by phase separation techniques, however these methods are generally only suitable for hydrophobic polymers. For example, polystyrene foams having densities of 0.02 to 0.20 g/cm^3 and cell sizes of 1-20 μm have been produced. Typically, a homogeneous polymer/solvent solution is first prepared. This solution is then permitted to phase separate by either dissolving a nonsolvent for

the polymer in the solution, decreasing the temperature to a point below the upper consolute solution temperature (UCST), or both. Most non-aqueous polymer/solvent systems capable of phase separating exhibit an UCST, and these polymers are typically hydrophobic. After phase separation, the temperature is further reduced to either below the freezing point of the solvent or below the glass transition temperature in order to lock in the desired structure. The solvent can then be removed from the porous, polymer structure either by freeze drying or supercritical drying to produce a microcellular foam. Unfortunately, simple evaporation of the solvent may not be employed for these products because large capillary forces at the liquid-vapor interface will cause the structure to shrink or crack, resulting in the destruction of the cells. In addition, although the expensive and tedious procedures of freeze-drying or supercritical drying may be employed, the resulting microporous foam will redissolve when brought into contact with a good solvent and melt when subjected to elevated temperatures.

Thus, there is a need for microcellular, open-celled foams which exhibit superabsorbency and can be readily synthesized from numerous polymer/solvent systems, particularly hydrophilic polymers.

SUMMARY OF THE INVENTION

While not exclusive, the following describes some of the important features and objects of the present invention.

It is an object of the present invention to provide a method for producing microporous, open-celled foam.

It is another object of the present invention to provide a method for producing microporous, open-celled foam which can be employed with numerous types of polymer/solvent systems.

It is yet another object of the present invention to provide microporous, open-celled foams, as well as a method for producing the same, wherein these foams which exhibit superabsorbancy, can be dried by a number of different methods, and which retain a significant amount of liquid even under pressure.

5 These foams will absorb and retain liquid by a combination of capillary action and pore wall swelling.

It is still another object of the present invention to provide a method for producing microporous, open-celled foam, wherein the properties of the foam can
10 be regulated by the choice of synthesis parameters.

The foregoing objects can be accomplished by providing a method for producing a microporous, open-celled foam, comprising the steps of (a) mixing a cross-linkable polymer and a first solvent to form a stable solution, preferably a
15 substantially homogeneous, single-phase solution, wherein the stable solution can be induced to phase separate (preferably upon a change in temperature of the solution); (b) inducing the stable solution to phase separate by into a polymer-concentrated phase and a polymer-dilute phase after a predetermined period of time; (c) inducing crosslinking of said polymer, so that the polymer will crosslink
20 in said concentrated phase for a predetermined period of time during the phase separation to thereby form a microporous material; and (d) drying the microporous material to produce the absorbent foam. Preferably, crosslinking is induced prior to the phase separation, and is permitted to continue for a predetermined period of time prior to phase separation. Optionally, the solution may be returned to a
25 single phase condition, and further crosslinked in this state to produce the desired foam. The single-phase solution may exhibit a lower consolute solution temperature or an upper consolute solution temperature, and phase separation is preferably induced by increasing or decreasing the temperature of the single-phase solution to a point above or below the lower consolute solution temperature or the
30 upper consolute solution temperature, respectively. If necessary, a phase-separation enhancer may be added to the single-phase solution prior to inducing phase separation so as to assist the stable solution to phase-separate, either in

conjunction with a temperature change or at a constant temperature. Suitable phase separation enhancers include other solutes such as a salt, other solvents, or even additional polymer. The foams may be dried by a number of different methods, and it is preferred that any uncrosslinked sol fraction be removed from the foam prior to drying.

Drying of the microporous materials produced by the methods of the present invention to produce the desired foams may be accomplished by air-drying, freeze-drying, or a solvent-exchange method. This latter method of drying is accomplished by placing the material in a second solvent, thereby replacing any of the synthesis (or "first") solvent which is present in the material with the second solvent. The microporous material may then be air-dried to evaporate the second solvent, or the solvent-exchange method repeated using a third solvent. It is preferable that if second and third solvents are employed that the second solvent be miscible with the synthesis solvent, and that the third solvent be miscible with the second solvent and a non-solvent for the polymer itself. In this fashion the third solvent will not be absorbed by the cell walls, and the evaporation process will not exert as great a force on the pores. It is also preferably that the second and third solvents (if employed) exhibit a high degree of volatility.

The synthesis method of the present invention may be employed with any polymer/solvent system which can be induced to phase separate, and wherein the polymer is crosslinkable. The polymer, for example, may be chosen from the following:

hydrophobically modified carbohydrate polymers, including: hydroxypropyl dextran, hydroxypropyl guar, hydroxypropyl starch, hydroxypropyl cellulose (HPC), hydroxyethyl cellulose (HEC), methyl cellulose, hydroxypropylmethyl cellulose, and ethylhydroxyethyl cellulose

poly(vinyl alcohol-co-vinyl acetate)
poly(methacrylic acid)

cyanoethylated or partially formalized poly(vinyl alcohol)
poly-N-vinyl-2-oxazolidone

polypeptides, including: poly(L-proline), and poly(valine-proline-glycine-X-
glycine), wherein X = any amino acid

acrylate (or analogous methacrylate) copolymers, including: hydroxypropyl
acrylate-co-acrylamide, diacetone acrylamide-co-hydroxyethyl acrylate, and
hydroxypropyl acrylate-co-hydroxyethyl acrylate

N-alkylacrylamide (or analogous N-alkylmethacrylamide) derivatives
including: ethylacrylamide, cyclopropylacrylamide, n-propylacrylamide,
and isopropylacrylamide.

The polymer is preferably HEC.

The crosslinker may be chosen from the following: acetaldehyde, formaldehyde,
glutaraldehyde, diglycidyl ether, divinyl sulfone, diisocyanates, dimethyl urea,
epichlorohydrin, oxalic acid, phosphoryl chloride, trimetaphosphate,
trimethylmelamine, polyacrolein, and ceric ion redox systems. Preferably, the
crosslinker is divinyl sulfone, when the polymer is either HPC or HEC.

There is also provided a method for producing a microporous, open-celled
foam, comprising the steps of: (a) mixing hydroxypropyl cellulose (HPC) and
water to form a substantially homogeneous, single-phase solution; (b) inducing
crosslinking of the HPC by adding a suitable crosslinking agent to the single-phase
solution; (c) inducing phase separation of the single-phase solution into a polymer-
concentrated phase and a polymer-dilute phase after a predetermined period of
time, wherein phase separation is induced by increasing the temperature of the
single-phase solution to above the lower consolute solution temperature of the
single-phase solution; and (d) permitting crosslinking to continue in the
concentrated phase after inducing phase separation to thereby form an open-celled

foam. The crosslinker is preferably divinyl sulfone (DVS). The concentration of HPC may be between about 1.9 and about 25 weight percent of the total weight of the single-phase solution, and is preferably about 4 weight percent. The pH of the single-phase solution should preferably be above about 11, and more preferably about 12. The molecular weight of the HPC employed is between about 100,000 and about 1,000,000, preferably about 400,000. The concentration of DVS is preferably between about 0.2 and about 5.5 weight percent of the single phase solution, and more preferably about 2 weight percent. Phase separation of these aqueous polymer solution can be induced by increasing the temperature of the solution to above about 40°C, preferably to a temperature of about 50°C. Phase separation may be induced after the crosslinking has proceeded for between about 1 and about 45 minutes (preferably about 5 minutes), and the crosslinking may be permitted to continue after inducing phase separation for between about 0.3 and about 100 hours (preferably about 24 hours). Excessive incubation at a high temperature and pH should be avoided, as it may cause polymer degradation.

A method for producing a microporous, open-celled foam, is provided, wherein this method comprises the steps of: (a) mixing hydroxyethyl cellulose (HEC), water and a phase-separation enhancer to form a substantially homogeneous, single-phase solution, wherein the phase-separation enhancer is chosen from the group consisting of: a salt, a water-soluble organic solvent, and a combination of a salt and a water-soluble organic solvent; (b) inducing crosslinking of the HEC by adding a suitable crosslinking agent to the single-phase solution; (c) inducing phase separation of the single-phase solution into a polymer-concentrated phase and a polymer-dilute phase after a predetermined period of time, wherein phase separation is induced by increasing the temperature of the single-phase solution to a point above the lower consolute solution temperature of the single-phase solution; and (d) permitting crosslinking to continue in the concentrated phase after phase separation is induced to thereby form an open-celled foam. The crosslinking agent is preferably divinyl sulfone (DVS), and the phase separation enhancer is preferably sodium chloride. Phase separation may be induced by increasing the temperature of the solution to above about 94°C,

preferably to about 95°C. The pH of the single-phase solution is preferably above about 11, and more preferably about 12. The concentration of HEC is preferably between about 1.3 and about 8 weight percent of the total weight of the single-phase solution and the DVS, more preferably about 3 weight percent. The
5 concentration of DVS is preferably between about 0.4 and about 2 weight percent, and more preferably about 1.6 weight percent. Phase separation may be induced after crosslinking has proceeded for between about 1 and about 3 minutes, preferably about 2.5 minutes. Crosslinking may then be permitted to continue, after phase separation is induced, for between about 20 and about 240 minutes,
10 and preferably for about 60 minutes.

The HPC and HEC foams produced by the methods described above may also be dried by the three methods previously described. If the solvent-exchange
15 method is employed, these foams may be dried using any of a number of second solvents including: methanol, ethanol, 1-propanol, 2-propanol, 1-butanol, sec-butanol, and acetone. If both a second and third solvent are employed in the drying process, the third solvent may, for example, be pentane, hexane or heptane. HPC and HEC foams are preferably dried by the solvent-exchange
20 process using an ethanol-pentane solvent system. Other solvents in addition to those specifically enumerated may also be employed, and the choice of solvent(s) do not appreciably affect the foam properties. It is preferred, however, that the final solvent employed prior to drying be a non-solvent for the polymer.

25 There is also provided an absorbent (preferably superabsorbent), microporous foam comprising a crosslinked polymer having interconnected fluid cells distributed throughout its mass, wherein the fluid cells have a diameter of between about 0.1 and about 100 μm , and wherein the foam can rapidly absorb at least about twice its dry weight in fluid. These foams preferably absorb and retain
30 fluid by a combination of capillary action and pore wall swelling. The foams also do not lose a significant amount of resorption capacity upon repeated swellin/drying cycles, and the polymers employed are preferably hydrophilic. The

polymers employed also preferably exhibit a lower consolute solution temperature (LCST) in an aqueous solution and phase separate from an aqueous solution as the temperature of the solution is increased to above said LCST. The polymer employed is preferably HPG or HEC.

5

DESCRIPTION OF THE PREFERRED EMBODIMENT

Applicants have discovered a method for producing microcellular, open-celled foams, which preferably exhibit superabsorbency. As used herein, an absorbent foam is one which absorbs at least twice its dry weight in fluid, and a superabsorbent foam is one which absorbs at least ten times its dry weight in fluid. Additionally, the resulting foams will swell, rather than dissolve, when placed in good solvents. The foams can be produced in any size or shape, and the method is readily applicable to numerous polymer/solvent systems which exhibit certain characteristics. The superabsorbent foams produced by the method of the present invention can be employed in any application wherein the foams of the prior art are used. In addition, the foams of the present invention can also be employed in biomedical applications (e.g., artificial blood vessels, tissue supports, implants, artificial skin, and controlled release drug delivery systems), packing for chromatography columns, reusable diapers, personal hygiene products such as tampons, and generally as a substitute for conventional superabsorbents. These foams can also be produced from hydrophilic polymers, thereby providing a product which is particularly suitable for biomedical applications since such products generally display good biocompatibility. Such hydrophilic foams will absorb and retain water by a combination of capillary action and swelling of the pore walls. The porosity and pore size of the foams can also be precisely controlled by varying the synthesis parameters.

Many homogeneous polymer/solvent solutions can be induced to phase separate into polymer-concentrated and polymer-dilute phases merely by a change in temperature. After the polymer is dissolved in a solvent, phase separation can

usually be induced by increasing the temperature to a point above the lower consolute solution temperature (LCST). Some polymer/solvent systems (particularly non-aqueous solvents) exhibit an upper consolute solution temperature (UCST), and thus in these systems phase separation is induced by decreasing the temperature to a point below the UCST. In addition, the LCST or UCST can be modified when needed by the addition of other solutes or solvents ("phase separation enhancer").

During the early stages of phase separation an interconnected morphology exists, and the applicants have found that open-celled, superabsorbent foams can be produced if this interconnected morphology can be preserved in the final product. Phase separation can also be induced by a number of other means while still producing the interconnected or bicontinuous structure during the phase separation. Typically, this interconnected structure is achieved merely by moving the polymer/solvent solution from a thermodynamically stable phase to a thermodynamically unstable condition. One skilled in the art can quite readily accomplish the phase separation merely by employing the polymer/solvent phase diagram for the particular polymer/solvent system employed. In addition to inducing phase separation by raising or lowering the temperature, the addition of a phase separation enhancer (with or without a change in temperature) may also induce phase separation. Suitable phase separation enhancers include: solutes such as salts, other solvents, additional polymer of the type used in the synthesis. If a solvent phase separation enhancer employed is a non-solvent for the polymer but is miscible with the solvent of the homogeneous polymer/solvent system, phase separation can be induced by spreading the enhancer over the surface of the polymer/solvent solution to form sheets or by dispersing the polymer/solvent solution in the enhancer to form particles. The phase separation enhancer can even be merely mixed with the polymer/solvent solution in order to induce phase separation. The use of a phase separation enhancer may also be combined with a change in solution temperature in order to induce phase separation, particularly when the phase separation is additional polymer.

The initial thermodynamically-stable state may even be in the form of a suspension or emulsion. The suspension or emulsion can then be induced to phase separate into a thermodynamically unstable condition by any of the methods described above, thereby providing a polymer-concentrated and a polymer-dilute phase.

In general, the foams of the present invention can be prepared from any polymer having reactive functional groups (i.e., can be crosslinked). The polymer is first solvated in order to form a stable, preferably homogeneous solution. The polymer is then preferably crosslinked in this stable solution for a predetermined period of time in order to form a limited crosslinked network, which can help provide a macroscopic structure for the final foam product. It should be noted, however, that crosslinking prior to phase separation may be omitted in some instances. The partially cross-linked, stable polymer solution is then induced to phase separate, usually by quickly changing the solution temperature, thereby resulting in interconnected polymer-concentrated and polymer-dilute phases. The polymer-concentrated phase is crosslinked into dense regions as the phase separation is occurring, thereby forming an open-celled network of crosslinked polymer with sol fraction occupying the cells. The crosslinked polymer-concentrated phase forms the cell walls, while the uncrosslinked, polymer-dilute phase is contained within the cells, thereby preserving the desired interconnected or bicontinuous structure. Complete phase separation cannot occur, however, because the crosslinking reaction freezes the desired microstructure. The extent of crosslinking in the phase-separated state can be varied, and the solution can even be returned to the homogenous state and the crosslinking continued if desired. The sol fraction is then removed, and the product dried, to produce the desired absorbent foam.

The process of the present invention can be performed using any polymer/solvent system which can be induced to phase separate, as long as the polymer is crosslinkable (i.e., has reactive functional groups). Typical functional groups which are easily reacted include hydroxyl, amine, carboxylic acid and

amino, however the present invention is not limited to these examples. Polymers which may be employed in the method of the present invention include:

1. Hydrophobically modified carbohydrate polymers, including:

5

hydroxypropyl dextran

hydroxypropyl guar

hydroxypropyl starch

hydroxypropyl cellulose

hydroxyethyl cellulose

10

methyl cellulose

hydroxypropylmethyl cellulose

ethylhydroxyethyl cellulose

2. Poly(vinyl alcohol-co-vinyl acetate)

3. Poly(methacrylic acid)

15

4. cyanoethylated or partially formalized poly(vinyl alcohol)

5. Poly-N-vinyl-2-oxazolidone

6. Polypeptides, including:

poly(L-proline)

20

poly(valine-proline-glycine-X-glycine), wherein X = any amino acid

7. Acrylate (or analogous methacrylate) copolymers, including:

hydroxypropyl acrylate-co-acrylamide

diacetone acrylamide-co-hydroxyethyl acrylate

25

hydroxypropyl acrylate-co-hydroxyethyl acrylate

8. N-alkylacrylamide (or analogous N-alkylmethacrylamide) derivatives, including:

ethylacrylamide

cyclopropylacrylamide

30

n-propylacrylamide

isopropylacrylamide

All of the polymers listed above can be readily crosslinked, and exhibit LCST behavior in aqueous solutions. Thus, these polymers can be used to prepare superabsorbent, microporous foams which rapidly absorb fluid by a combination of capillary force and pore wall swelling.

5

Any crosslinker suitable for the particular polymer/solvent system employed can be used, particularly the types used to produce conventional superabsorbents from polymers such as starch (e.g., divinyl sulfone). These crosslinking agents are generally di- or multi-functional crosslinking agents which react with the pendant polymer functional groups. Suitable crosslinking agents include:

10

acetaldehyde

formaldehyde

glutaraldehyde

15

diglycidyl ether

divinyl sulfone

diisocyanates

dimethyl urea

epichlorohydrin

20

oxalic acid

phosphoryl chloride

trimetaphosphate

trimethylomelamine

polyacrolein

25

ceric ion redox systems

Other known crosslinking means may be employed, including photo-crosslinking, as well as other "physical" crosslinking means. By physical crosslinking it is meant that the crosslinking occurs by non-covalent bonding, whereas chemical crosslinking (e.g., by the list of crosslinkers set forth above) results in the formation of new covalent bonds within the product. Physical crosslinking can occur due to non-covalent hydrophobic interactions between

30

hydrophobic polymer side chains of a polymer. This effect can often be enhanced by the addition of a surfactant, and the term crosslinker in the context of the present application is considered to include such surfactants (a physical crosslinking agent). One such polymer which can be crosslinked in this manner is hydrophobically modified hydroxyethyl cellulose (HMHEC) (available from Aqualon Co., Wilmington, DE, as Natrosol Plus®). Other types of physical crosslinking include hydrogen-bonding, van der Waals interactions, ionic bonding, hydrogen bonding, coordination interactions, and salt bridges. The present invention is considered to include crosslinking by any of these physical methods, and these types of crosslinking are set forth in further detail in *Absorbent Polymer Technology*, edited by L. Brannon-Peppas and R.S. Harland, Elsevier Science Publishing Co. Inc., New York (1990).

After the product has been permitted to phase separate while crosslinking for a predetermined period of time (a time sufficient to provide strength to the final foam product), the product must be dried in order to produce a microporous material suitable for use as an absorbent foam. The sol fraction may be removed from the product by any of a number of means, but preferably merely by leaching the sol from the microporous material using the same solvent employed in the synthesis reaction (e.g., water). The product may then be air-dried at room temperature, or even in a conventional or microwave oven, in order to evaporate the solvent and produce a foam. Freeze-drying (any conventional means) or solvent-exchange may also be utilized.

The properties of the foams produced by the methods of the present invention can be readily tailored to one's needs, and one skilled in the art would be able to readily prepare suitable foams from any polymer/solvent system wherein said system can be induced to phase separate and wherein said polymer is crosslinkable. Polymer/solvent phase diagrams are readily available in the literature, or can be easily prepared in the laboratory. Suitable crosslinkers for polymers are also well-known, and thus one skilled in the art could readily identify a crosslinker suitable for the polymer/solvent solution employed. For the

preferred polymers which exhibit a LCST in aqueous solutions, selection criteria are set forth in the work by L.D. Taylor and L.D. Cerankowski, J. Polymer Science: Polymer Chemistry Edition, Vol. 13, pp. 2351-2570 (1975). In fact, the authors of this work stated that "the LCST phenomenon, rather than being a rare curiosity, is quite predictable and easy to achieve." Even polymers which are extremely hydrophilic (totally miscible in water at all temperatures) can be modified to the point that they exhibit LCST behavior. This can be accomplished, for example, by merely copolymerizing the precursor monomer with a more hydrophobic monomer (e.g., acrylamide with hydroxypropyl acrylate) to produce a crosslinkable polymer which exhibits the desired LCST behavior. It should be pointed out that, even though the copolymer exhibits LCST behavior, it is still relatively hydrophilic and therefore the resultant foam will absorb and retain water by a combination of capillary forces and pore wall swelling.

The properties of the superabsorbent foams will depend upon a number of factors, including: precursor polymer type, molecular weight of the polymer, initial polymer concentration, crosslinker concentration, pH of the polymer/solvent solution, reaction time prior to phase separation and reaction time during and after phase separation. By varying these parameters, the properties of the foams produced can be tailored to one's needs. The most significant properties of these foams include: porosity, sorption capacity, sorption rate, pore size, pore wall thickness, and compression strength. The synthesis parameters of the method of the present invention can be readily adjusted by one skilled in the art in order to produce a foam of the desired properties, particularly the desired rigidity. For example, increasing the initial polymer concentration will decrease the porosity of the foam while increasing the strength of the foam. Pore sizes can be reduced by increasing the amount of crosslinking which occurs prior to phase separation. Pore size (as well as pore wall thickness) will also decrease with corresponding increases in the initial polymer concentration, molecular weight of the polymer, or crosslinker concentration. Crosslinking during phase separation should, however, proceed for a time sufficient to ensure that the foam product will not collapse significantly under a modest load.

In general, the foams of the present invention are superabsorbent, and their improved properties over that of the prior art are due, in part, to the fact that these foams absorb and retain liquid not only by capillary action, but also by a swelling of the pore walls. Unlike prior art foams, foams can be produced by the method of the present invention which can be air-dried while still producing a foam with good structural properties.

EXAMPLE 1

Hydroxypropyl cellulose (HPC) (available from Aldrich Chemical Co.) was dissolved in an aqueous NaOH solution. An alkaline pH was maintained in order to catalyze the crosslinking reaction. This solution was then maintained in a glass vial at room temperature for at least 24 hours in order to ensure complete and uniform hydration of the polymer. A predetermined amount of divinyl sulfone (DVS) was then added, and the solution was mixed thoroughly for approximately 30 seconds.

The polymer/crosslinker solution was next poured onto a glass plate (6"x6"x0.12") between silicone rubber gaskets (1.6 mm thick), and then covered with a second glass plate. The plates were secured to one another using spring-loaded clamps, thereby forming a sealed mold containing the polymer/crosslinker solution. The crosslinking reaction was then permitted to proceed at room temperature for a predetermined period of time (reaction time before phase separation). The mold was next immersed in a constant temperature bath which was maintained above the LCST of the polymer/solvent solution. The polymer/solvent solution then began to phase separate, and the polymer-dense phase was crosslinked as the solution phase separated and thereafter.

After a predetermined period of time, the mold was removed from the bath and opened, and the sheet of microporous material was removed. The sheet was then soaked in water in order to leach out the sol fraction which contained small amounts of polymer and crosslinker which were not incorporated into the foam

network. The sheets were next dried in air either at room temperature or at high temperature in an oven (either conventional or microwave) to produce the microporous foams. At room temperature the water-swollen sheets took approximately 10-20 hours to dry completely. Table 1 provides the synthesis parameters for the HPC foams produced according to this procedure.

The sheets can be air-dried more quickly by first replacing the water held within the water-swollen foam with a more volatile solvent such as heptane. Heptane, however, is immiscible in water, and thus the water-swollen sheets were first soaked in ethanol to replace the water. The ethanol-soaked sheets are then soaked in heptane, thereby replacing the ethanol with heptane. While the heptane will remove ethanol from the cell walls, it does not itself swell the pore walls because heptane is a non-solvent for HPC. Thus, the heptane-swollen sheets can be air-dried at room temperature in about 10 to 20 minutes. Various other solvent combinations may be employed as part of the drying process, and a single solvent drying method can certainly be employed also (i.e., drying directly after soaking the sheet in the second solvent). The solvent used in the drying process (the "second" solvent) should, however, be miscible with the solvent employed for the foam synthesis so that it will fully replace the synthesis solvent. If a third solvent is employed for the drying process (e.g., heptane), it should be miscible with the second solvent and a non-solvent for the polymer. In this manner, the pore walls will be free of solvent, and the foam will dry more quickly. One advantage of this solvent-exchange method is that the third solvent, since it does not swell the cell walls, will exert little pressure on the pores as it evaporates, thereby minimizing any loss of porosity caused by drying.

EXAMPLE 2

In order to examine foam properties and the effect of the various synthesis parameters of Table 1 on these properties, several tests were performed on the foams synthesized in Example 1. The porosity of the foam is defined as the ratio of the mass of water which can be mechanically squeezed from a water-swollen

foam to the mass of the water-swollen foam (at 25° C). This testing indicated that some water was retained within the pore walls, thereby swelling the polymer network itself, while water held within the micropores was forced out by the mechanical pressure.

5

The sorption capacity of the foam is defined as the ratio of the mass of the water-swollen foam to the mass of the dry foam (at 25 °C). In order to determine the effect of drying conditions on the ability of the foam to absorb water, the sorption capacity was determined both before and after the initial drying of the foam. The porosity and sorption capacity of the foams are shown in Table 2 below.

10

The results in Table 2 indicate that all of the foams absorbed many times their own weight in water, and a portion was retained in the pore walls even after the foams were mechanically compressed. One foam sample (F 22) was even capable of absorbing more than 40 times its weight in water. In addition, drying the foams did not significantly affect their ability to reabsorb fluid. The data in Table 2 also indicates that the porosity of the foam generally increases with a decrease in the initial polymer concentration. Other trends are also apparent from the data shown above. Sample F19 did not expel any water under the application of mechanical force, and this was probably due to a lack of pore interconnectivity or small pore size. This is readily resolved, however, merely by, for example, reducing the reaction time prior to phase separation. Samples F01 and F27 were too fragile to characterize by Applicants' techniques.

15

20

TABLE 1

Sample Number	Average Mol. Wt of Polymer	Initial Polymer Conc. (wt%)	Initial Crosslinker Conc. (wt%)	pH of Initial Solution	Phase Separation Temp. (°C)	Rxn. Time Before Phase Separation (min)	Rxn. Time During Phase Separation (hr)
F 01	100,000	4.66	2.18	12.30	46.5	3.0	16.0
F 02	370,000	4.66	2.18	12.30	46.5	2.5	17.5
F 03	1,000,000	4.66	2.18	12.30	46.5	3.0	19.5
F 04	1,000,000	3.76	2.18	12.30	46.5	3.0	19.0
F 05	1,000,000	2.88	1.12	12.30	46.5	3.0	24.0
F 08	100,000	8.95	1.57	11.43	46.5	3.0	20.0
F 09	100,000	8.95	1.57	11.43	45.0	6.1	19.0
F 10	100,000	8.95	2.10	11.87	60.0	2.0	24.0
F 12	370,000	4.66	2.18	12.30	60.0	1.8	19.0
F 13	370,000	4.66	2.18	12.30	70.0	1.9	20.0
F 14	370,000	4.66	5.29	12.30	79.8	1.3	23.0
F 15	370,000	4.66	2.18	12.30	60.0	21.2	17.0
F 16	370,000	4.71	1.11	12.30	60.0	21.2	23.0
F 17	370,000	4.66	2.18	12.30	60.0	10.7	23.0
F 19	1,000,000	3.80	1.11	12.30	46.5	40.4	23.0
F 20	370,000	3.80	1.12	12.30	46.5	40.4	23.0
F 21	370,000	2.88	1.12	12.30	46.5	40.4	19.5
F 22	370,000	1.94	1.12	12.30	46.5	40.4	21.0
F 23	100,000	3.80	2.20	12.30	46.5	40.4	20.0
F 27	370,000	2.90	0.28	12.30	46.5	40.4	22.5
F 28	370,000	2.90	0.56	12.30	46.5	40.4	22.0
F 41	100,000	8.95	1.57	12.30	40.0	2.0	23.0
F 42	100,000	8.95	1.57	12.30	46.5	2.0	25.0
F 43	370,000	5.60	1.09	12.30	42.0	5.7	24.0
F 44	370,000	5.60	1.09	12.30	40.0	6.0	24.0
F 45	370,000	5.60	1.09	12.30	46.5	5.5	24.0
F 46	370,000	4.66	2.18	11.43	46.5	2.4	24.0
F 47	370,000	4.66	2.18	11.43	46.5	10.7	24.0
F48	100,000	4.66	2.18	11.43	46.5	10.7	100.00
P18	100,000	12.66	2.98	12.30	46.5	1.8	23.5
P17-S1	100,000	12.66	2.98	12.30	46.5	1.8	0.33

TABLE 2

Sample Number	Porosity	Sorption Capacity of Foam (never dried) (g wet/g dry)	Sorption Capacity of Foam (after drying) (g wet/g dry)
F 01	-	-	-
F 02	0.86	18	17
F 03	0.81	16	-
F 04	0.84	18	20
F 05	0.86	-	27
F 08	0.75	13	14
F 09	0.69	10	10
F 10	0.78	12	12
F 12	0.87	24	25
F 13	0.85	25	26
F 14	0.82	19	20
F 15	0.79	18	18
F 16	0.79	18	20
F 17	0.85	18	19
F 19	-	18	-
F 20	0.72	23	-
F 21	0.87	34	22
F 22	0.91	42	44
F 23	0.86	25	24
F 27	-	-	-
F 28	0.91	36	33
F 41	0.70	13	13
F 42	0.81	11	12
F 43	0.81	18	19
F 44	0.77	21	21
F 45	0.85	18	19
F 46	0.81	20	21
F 47	0.80	22	22
F 48	0.76	13	14
P18	0.58	-	6.2
P17-S1	-	-	6.5

TABLE 2

Sample Number	Porosity	Sorption Capacity of Foam (never dried) (g wet/g dry)	Sorption Capacity of Foam (after drying) (g wet/g dry)
F 01	-	-	-
F 02	0.86	18	17
F 03	0.81	16	-
F 04	0.84	18	20
F 05	0.86	-	27
F 08	0.75	13	14
F 09	0.69	10	10
F 10	0.78	12	12
F 12	0.87	24	25
F 13	0.85	25	26
F 14	0.82	19	20
F 15	0.79	18	18
F 16	0.79	18	20
F 17	0.85	18	19
F 19	-	18	-
F 20	0.72	23	-
F 21	0.87	34	22
F 22	0.91	42	44
F 23	0.86	25	24
F 27	-	-	-
F 28	0.91	36	33
F 41	0.70	13	13
F 42	0.81	11	12
F 43	0.81	18	19
F 44	0.77	21	21
F 45	0.85	18	19
F 46	0.81	20	21
F 47	0.80	22	22
F 48	0.76	13	14
P18	0.58	-	6.2
P17-S1	-	-	6.5

Pore sizes were measured by conventional scanning electron microscopy (SEM), and the samples examined by this method were dried using the solvent-exchange method. Pore sizes were estimated from the size of the dark, roughly circular regions in the SEM micrographs, while pore struts were estimated from the size of the light, roughly linear areas. The results of SEM analysis are shown in Table 3 below. Applicants found that some of the foam samples tended to collapse to varying degrees upon conventional drying, however these foams would nevertheless fully swell when rehydrated. Applicants further found, however, that pore collapse could often be prevented by using a freeze-drying technique. The freeze-drying technique merely ensured a fully-expanded pore structure would exist for the SEM measurements, as virtually no structural collapse occurs. Additionally, freeze-drying does not significantly alter the equilibrium sorption properties of the foam. The foam samples were plunged into a dry-ice/ethanol slush until frozen. The samples were then transferred to a glass container and lyophilized at a pressure of less than 1 mmHg at -15°C for at least 15 hours.

TABLE 3

Sample Number	Pore Size (μm)	Strut Size (μm)	Sample Number	Pore Size (μm)	Strut Size (μm)
F 01	0.5 - 20	0.5 - 1.0	F21	0.1 - 0.5	0.07 - 0.15
F 02	0.2 - 2.5	0.2 - 0.6	F 22	0.1 - 0.8	0.1 - 0.2
F 03	0.1 - 0.3	-	F 23	0.06 - 0.4	0.06 - 0.3
F 04	0.1 - 0.5	0.1 - 0.3	F 27	0.2 - 2.0	0.2 - 0.4
F 05	0.1 - 0.7	0.1 - 0.5	F 28	0.2 - 1.5	0.1 - 0.3
F 08	1.0 - 15	1.5 - 2.5	F 41	0.5 - 17	1.0 - 3.0
F 09	10-100 & 3-5	25-100 & 1.5-5	F 42	0.5 - 9.0	0.5 - 2.5
F 10	0.6 - 6.0	0.5 - 2.0	F 43	0.1 - 2.0	0.1 - 0.2
F 12	0.3 - 2.0	0.1 - 0.6	F 44	0.1 - 2.0	0.2 - 0.6
F 13	0.3 - 3.0	0.1 - 0.6	F 45	0.2 - 1.5	0.1 - 0.5
F 14	-	-	F 46	0.2 - 4.0	0.3 - 1.0
F 15	closed pores	closed pores	F 47	0.2 - 5.0	0.3 - 1.0
F 16	0.1 - 0.5	0.1 - 0.3	F 48	15-50 & 2-5	15-50 & 2-7
F 17	0.1 - 0.5	0.1 - 1.0	P18	0.5 - 5	1 - 2
F19	closed pores	closed pores	P17-S1	0.4 - 7	-
F20	closed pores	closed pores			

Most of the foam samples exhibited randomly interconnected polymer-dense regions (struts) with interconnected void spaces between them (pores). There were no distinct windows between the pores, and thus the foams were of the desired, "open-cell" variety. The molecular weight of the polymer greatly affects the pore size, as the pore size decreases drastically as the polymer molecular weight increases. This is likely due to the increased viscosity of the solutions as the molecular weight increases, which in turn reduces the phase separation rate. While some of the samples exhibited closed pores, a few of these were able to still function as superabsorbent foams (such as sample F15). This problem, however, can be eliminated merely by a minor change in the synthesis parameters for the foam, and could readily be accomplished by one skilled in the art.

EXAMPLE 4

In order to measure the ability of the foams to retain fluid under an applied pressure, creep tests were performed. Water-swollen foams were placed between two thin wire mesh screens, and this sandwich was then placed between flat plates connected to a strain gauge. A pressure of 0.75 psi (1.0 psi for some samples) was then applied to the sample until the thickness of the foam no longer decreased. The weight of the compressed foam was then compared to the weight of the swollen foam before application of the load in order to determine the percent of water retained by the foam under an applied pressure. Creep test measurements are shown in Table 4.

TABLE 4

Sample Number	Percent Retention of Free-Swelling Capacity @ 0.75 psi (w/w%)	Sample Number	Percent Retention of Free-Swelling Capacity @ 0.75 psi (w/w%)
F 01	-	F 20	53
F 02	61 (@ 1.0 psi)	F 21	36
F 03	61 (@ 1.0 psi)	F 22	25
F 04	53 (@ 1.0 psi)	F 23	50
F 05	-	F 27	36
F 08	79	F 28	43
F 09	95	F 41	85
F 10	94	F 42	96
F 12	63	F 43	77
F 13	62	F 44	72
F 14	62	F 45	80
F 15	77	F 46	66
F 16	66	F 47	65
F 17	72	F 48	80
F 19	-		

As shown above, the foams produced by the method of the present invention exhibited excellent water retention under a considerable pressure. In fact, some of the foams retained over 90% of their absorbed water under a pressure of 0.75 psi. This is significant in that fluid retention under this magnitude of pressure is a highly-desirable property in applications such as
5 diapers.

EXAMPLE 5

10 Direct wicking height measurements of the foam are impractical because such tests would require rather long strips of foam (10-50 cm), and thus an alternate method described in *Absorbency*, (edited by P.K. Chatterjee (Elsevier, 1985)) was employed. In this approach, the dry foam is contacted with a liquid such that absorption occurs under varying negative hydrostatic pressure. In order
15 to ensure that an intact microstructure was maintained for all of the samples, however, a modified solvent-exchange drying technique was employed for the samples used in the wicking tests. Water was first expelled from the newly-synthesized foam by pressing the foam between absorbent tissues. The foam was then immersed in acetone for at least 20 minutes, thus stripping the pore walls of
20 any remaining water. The acetone-swollen foam was then immersed in heptane for at least 40 minutes. While the heptane removed the acetone from the cell walls, it did not itself swell the pore walls because heptane is a non-solvent for HPC. The heptane was then readily removed from the pores by air-drying the foam for 10-20 minutes.

25 The wicking experiments were performed using a fritted glass filter plate placed in a funnel. The bottom of the funnel was connected to one end of a vertical, water-filled tube, and the other end of the tube was placed in a water reservoir. The length of the tube was either 10cm or 30 cm, and the microporous
30 glass frit had sufficient capillary pressure to support the column of liquid in the

5. tube. The dry foam was then placed on the fitted glass plate where it was able to absorb water. The tube in this apparatus essentially acts as a substitute for a corresponding length of saturated foam through which the water would have wicked. The wicking ability of the foam was measured as the ratio of the weight of the water-swollen foam to the weight of the dry foam. The wicking test results are shown in Table 5.




TABLE 5

Sample Number	Sorption Capacity of Foam	
	@ 30 cm H ₂ O (.43 psi) (g wet/g dry)	@ 10 cm H ₂ O (.14 psi) (g wet/g dry)
F 01	5	6
F 02	12	15
F 03	9	12
F 04	9	12
F 05	8	10
F 08	7	10
F 09	8	9
F 10	11	11
F 12	8	13
F 13	7	11
F 14	9	13
F 15	13	17
F 16	12	17
F 17	11	15
F 19	-	-
F 20	-	-
F 21	8	14
F 22	7	9
F 23	11	21
F 27	7	10
F 28	7	10
F 41	9	12
F 42	10	11
F 43	12	16
F 44	10	18
F 45	11	16
F 46	9	14
F 47	7	10
F 48	-	-

While the wicking height (i.e., the height of water supported) is less than expected based upon the pore sizes measured by SEM, the results do indicate that the foams will retain fluid under a modest negative hydrostatic pressure. The results in Table 5 would also tend to indicate that the pores are not actually draining, but rather are collapsing while remaining water-filled. In other words, a portion of the fluid held by capillary action is released, while that held within the pore walls is retained. In this fashion, the behavior of the foams synthesized by the methods of the present invention lies between that typically exhibited by non-porous gels and that exhibited by conventional, porous solids. Further wick testing at varying water heights indicated that fluid retention remained relatively constant at heights greater than 30 cm H₂O, and a significant amount of fluid was retained by most of the foams at wicking heights as great as 60 cm H₂O.

Example 6

The rate of sorption of the various foams was determined by placing a flat, dry foam sample on the surface of a dish of water. The foam samples used in this test were dried using the solvent-exchange method of Example 5. The time for the sample to completely swell was recorded, and the sample was then removed and weighed. The completeness of the swelling process was measured by either returning the sample to the dish of water for additional time and thereafter remeasuring the sample weight, or by comparing the measured weight with that obtained for a fully-swollen sample. The sorption rates are shown in Table 6, and vary from about 2 seconds to over half an hour. All of these sorption rates, however, are significantly shorter than prior art superabsorbents produced as sheets of a comparable size from the identical polymer.

TABLE 6

Sample Number	Sorption Time (sec)	Sample Number	Sorption Time (sec)
F 01	9	F 20	-
F 02	4	F 21	> 900
F 03	240	F 22	> 1320
F 04	20	F 23	2000
F 05	95	F 27	210
F 08	9	F 28	420
F 09	6	F 41	5
F 10	5	F 42	3
F 12	5	F 43	10
F 13	15	F 44	25
F 14	4	F 45	8
F 15	300	F 46	5
F 16	90	F 47	28
F 17	5	F 48	2
F 19	-		

Example 7

In order to examine the effect of the drying method on the foam properties, three foam samples of relatively high sorption capacity (F12, F13 and F17) were dried by the three methods described previously (air-drying, solvent-exchange, and freeze-drying). The water-swollen foam samples which were air-dried were first pressed between layers of absorbent material to remove water present in the pores. The foams were then air dried (@ 26 °C) completely in 2-3 hours. These air dried samples appeared either transparent or translucent (as opposed to milky white) with little or no air-filled pores present. It was thus apparent that this drying technique caused the pores present in the foam to collapse (to a non-porous state, rather than a porous state). Even the air-dried samples absorbed a

considerable amount of water, however, and the sorption capacity of the foam was not significantly affected by the manner of drying. The rate of sorption was affected, however, and the results are shown below in Table 7.

TABLE 7

Sample Type	Air-Dried (sec)	Solvent-Exchange (sec)	Freeze-Dried (sec)
F 12	45	5	2100
F 13	60	15	3300
F 17	38	5	300

While the sorption times for the air-dried samples were significantly greater than those dried by the solvent-exchange method, they were still less than a minute. Although the freeze-dried samples took considerably longer to swell, however, most of the absorption in the freeze-dried samples took place rather quickly (at a rate comparable to the other samples). Thus, freeze-dried samples F12, F13 and F17 absorbed 20, 15, and 17 times their dry weights in only 30, 35 and 12 seconds, respectively. While the reason for this anomaly is unclear, it is believed that freeze-drying may have "over-dried" the foam, thereby removing molecularly bound water from the polymer and enhancing polymer-polymer attraction in the dry state.

Example 8

Since commercially available HPC has a relatively high degree of substitution (> 2.5), and therefore does not readily biodegrade, foams were produced from high viscosity hydroxyethyl cellulose (HEC) (Aldrich Chemical Co.) using the same techniques described previously. Commercially-available HEC has a lower degree of substitution (0.9-1.0), and therefore the resultant

foams would be expected to biodegrade more quickly than a foam made from HPC.

5 While an aqueous HEC solution does not exhibit an LCST, and therefore does not phase separate upon heating, it is known that the addition of a solute such as a salt can lower the LCST of an aqueous polymer solution. Applicants found that by saturating an aqueous solution of HEC with sodium chloride (about 24 wt% salt), the solution exhibited an LCST of less than 95 °C. Thus, when the temperature of such a salt-saturated polymer solution was increased to at least
10 about 95 °C, the solution phase-separated, and thus was amenable to the method of the present invention.

Table 8 below provides the synthesis parameters for HEC foams produced by the method of the present invention. It should be noted that if sufficient
15 amounts of crosslinker were not present, a sufficient interconnected structure would not be formed. For example, a crosslinker level significantly below about 0.40 wt. % did not produce a foam with the synthesis parameters of samples F61 and F62. The procedures employed for the examples of Table 8 were identical to those previously described (synthesis at pH 12.3), however the sheets were
20 repeatedly swelled in water to ensure a complete removal of the sol fraction and salt present in the foam. The sheets were then dried using the solvent-exchange method described previously in order to ensure that the foam structure did not collapse. The solvents preferably employed for HEC foam drying are ethanol, followed by pentane, however numerous other solvents could be employed.

TABLE 8

Sample Number	Initial Polymer Conc. wt %	Initial Conc. wt %	Na Cl Conc. wt %	Phase Separation Temp °C	Rxn. Time before Phase Separation (sec)	Rxn. Time During Separation (hours)
F 61	6.87	0.40	24.0	98.7	240	7.5
F 62	6.87	0.40	24.0	98.7	195	6.5
F 53	3.46	1.62	25.6	94.9	156	1.0
F 98	3.51	1.64	25-27.7%	95.7	126	0.32
F 96	3.50	1.67	25-27.7%	95.0	150	24
F 97	2.83	1.67	25-27.7%	95.0	156	1.03

In order to characterize the HEC foams, tests similar to those previously described for HPC foams were employed. The results of these tests are shown in Table 9. It should be noted that foam F52 was too weak to be properly characterized by the test methods employed.

TABLE 9

Sample Number	Sorption Capacity g wet/ g dry	Percent Retention of Free Swelling Capacity (w/w%) (creep test)	Sorption Capacity @ 50 cm H ₂ O g wet/ g dry (wicking test)	Sorption Time (sec)
F 61	16	-	-	-
F 53	17	88 (@ 0.75psi)	15	9
F 98	18	-	15	8
F 96	no foam formed	-	-	-
F 97	26	-	14	12

From the results shown in Table 9, it is apparent that HEC foams generally have better fluid retention and wicking properties than comparable HPC foams. It should be noted that sample F96 was permitted to crosslink for too long a period

of time, and the high temperature and pH caused the foam to degrade into a polymer solution. One skilled in the art, however, can easily rectify this problem by reducing the reaction time during phase separation.

5 In addition, stress-strain measurements on the two foam types (using a Rheometrics RSA-II solid analyzer) revealed that the HEC foams were considerably stronger than comparable HPC foams. This is likely due to more efficient crosslinking of HEC. More importantly, however, this testing demonstrated that the principles of foam synthesis garnered from the production of
10 HPC foams can be generalized to other polymer/solvent systems, wherein the solution can be induced to phase separate. In the case of HEC/water, the addition of sodium chloride produces the desired phase separation mechanism. The addition of other solutes or solvents will produce similar effects on phase separation to varying degrees.

15 As expected, granulation of HEC foams also had a marked effect on the sorption rates, as these rates were even less than those given in Table 9. While the absorbance under load for the granulated foams were less than that for foam sheets, applicants believe that these results were due to inadvertent improper
20 drying of the samples used for these tests.

 Applicants have found that the superabsorbent foams produced by the methods of the present invention have a sorption rate which is at least 100 times faster than a conventionally-made, non-porous superabsorbent sheet of comparable
25 size made, even wherein the non-porous superabsorbent is made from the very same polymer as the foam.

 In addition, as noted above, conventional, non-porous superabsorbents (e.g., commercially-available, superabsorbent poly(sodium acrylate)) are usually
30 granulated in order to improve their swelling capacity and sorption rate. These

conventional superabsorbents, however, must also be mixed with a fluff material because of the gel blocking phenomenon. The fluff wicks the fluid to the non-porous, superabsorbent, where the fluid is absorbed. The use of this fluff, however, significantly increases the thickness of the absorbent layer of a product such as a diaper. Applicants have found that their microporous, superabsorbent foam sheets have at least the same swelling capacity, and a comparable sorption rate, as a conventionally-made, non-porous superabsorbent which has been ground and combined with fluff (even if Applicants' foam and the conventional superabsorbent are produced from the very same polymer). Applicants' foams are able to wick fluid into the interior of the foam without blocking the spaces between absorptive polymer regions, unlike the conventional, non-porous superabsorbents. Obviously, a thin, superabsorbent sheet, with no additional fluff, is particularly advantageous in products such as diapers and feminine hygiene devices. Sorption kinetics for conventional, non-porous, superabsorbents are available, for example, in *Kinetics of Swellin of Absorbent Polymers*, F.L. Buchholz. It should be pointed out that when the foams of the present invention are to be used for absorbing aqueous solutions (e.g., in diapers), it is essential that a hydrophilic polymer be employed in the synthesis. Applicants' foams also do not significantly lose their desired sorption properties (e.g., capacity and rate) even after repeated drying and resorption of fluid. In addition, Applicants' foams can be flattened in the dry state while still retaining the ability to absorb fluid and expand.

It will be understood that modifications may be made in the present invention without departing from the spirit of it. For example, various other types of polymers, solvents and crosslinkers other than those specifically disclosed may be effectively employed to practice the process of the present invention. Thus, the scope of the present invention should be considered in terms of the following claims, and is understood not to be limited to the details of structure and operation shown and described in the specification.

What we claim is:

1. A method for producing a microporous, absorbent foam, comprising the steps of:

- (a) mixing a cross-linkable polymer and a first solvent to form a stable solution, wherein said stable solution can be induced to phase separate;
- 5 (b) inducing said stable solution to phase separate into a polymer-concentrated phase and a polymer-dilute phase after a predetermined period of time;
- (c) inducing crosslinking of said polymer, so that said polymer will crosslink in said concentrated phase for a predetermined period of time
- 10 (d) drying said microporous material to produce said absorbent foam.

2. The method of claim 1, wherein said stable solution is a substantially homogeneous, single-phase solution.

3. The method of claim 2, wherein said phase separation is induced by changing the temperature of said stable solution.

4. The method of claim 2, wherein said phase separation is induced by adding a phase separation enhancer to said stable solution.

5. The method of claim 4, wherein said phase separation enhancer is either another solute or an additional solvent, and wherein said additional solvent is a non-solvent for said polymer and is miscible with said first solvent.

6. The method of claim 3, wherein said crosslinking is induced prior to said phase separation, and wherein said crosslinking is permitted to proceed for a predetermined period of time prior to said phase separation.

7. The method of claim 3, wherein said single-phase solution exhibits a lower consolute solution temperature, and wherein said phase separation is induced by increasing the temperature of said single-phase solution to a point above said lower consolute solution temperature.
8. The method of claim 3, wherein said single-phase solution exhibits an upper consolute solution temperature, and wherein said phase separation is induced by decreasing the temperature of said single-phase solution to a point below said upper consolute solution temperature.
9. The method of claim 3 further comprising the step of adding a phase-separation enhancer to said single-phase solution prior to inducing said phase separation.
10. The method of claim 3, further comprising the step of removing the uncrosslinked sol fraction present in said microporous material prior to said drying step.
11. The method of claim 3, wherein said drying step is accomplished by air-drying.
12. The method of claim 3, wherein said drying step is accomplished by freeze-drying.
13. The method of claim 3, wherein said drying step is accomplished by placing said microporous material in a second solvent, thereby swelling said material with said second solvent and replacing any of said first solvent which is present in said material, followed by air-drying said material so that said second solvent will evaporate.

14. The method of claim 13, wherein said drying step further comprises the step of placing said microporous material swollen with said second solvent in a third solvent, thereby replacing said second solvent with said third solvent, and thereafter air-drying said material so that said third solvent will evaporate.

15. The method of claim 3, wherein said polymer is chosen from the group consisting of: hydrophobically modified carbohydrate polymers, poly(vinyl alcohol-co-vinyl acetate), poly(methacrylic acid), cyanoethylated or partially formalized poly(vinyl alcohol), poly-N-vinyl-2-oxazolidone, polypeptides, acrylate (or analogous methacrylate) copolymers, and
5 N-alkylacrylamide (or analogous N-alkylmethacrylamide) derivatives.

16. The method of claim 15, wherein said hydrophobically modified carbohydrate polymers include: hydroxypropyl dextran, hydroxypropyl guar, hydroxypropyl starch, hydroxypropyl cellulose (HPC), hydroxyethyl cellulose (HEC), methyl cellulose, hydroxypropylmethyl cellulose, and ethylhydroxyethyl
5 cellulose; wherein said polypeptides include: poly(L-proline), and poly(valine-proline-glycine-X-glycine), wherein X = any amino acid; wherein said acrylate (or analogous methacrylate) copolymers include: hydroxypropyl acrylate-co-acrylamide, diacetone acrylamide-co-hydroxyethyl acrylate, and hydroxypropyl acrylate-co-hydroxyethyl acrylate; and wherein said N-alkylacrylamide (or
10 analogous N-alkylmethacrylamide) derivatives include: ethylacrylamide, cyclopropylacrylamide, n-propylacrylamide, and isopropylacrylamide.

17. The method of claim 16, wherein said polymer is either HPC or HEC.

18. The method of claim 3, wherein said crosslinking is accomplished by chemical means.

19. The method of claim 3, wherein said crosslinking is accomplished by physical means.
20. The method of claim 18, wherein crosslinking is induced by adding a suitable crosslinking agent to said solution.
21. The method of claim 18, wherein said solution is photo-crosslinked.
22. The method of claim 19, wherein said physical crosslinking is accomplished by employing a polymer having hydrophobic polymer side chains capable of interacting with one another.
23. The method of claim 19, wherein said physical crosslinking is accomplished through hydrogen-bonding, van der Waals interactions, ionic bonding, hydrogen bonding, coordination interactions, or salt bridges.
24. The method of claim 18, wherein said crosslinking agent is chosen from the group consisting of: acetaldehyde, formaldehyde, glutaraldehyde, diglycidyl ether, divinyl sulfone, diisocyanates, dimethyl urea, epichlorohydrin, oxalic acid, phosphoryl chloride, trimetaphosphate, trimethylmelamine, polyacrolein, and ceric ion redox systems.
25. The method of claim 24, wherein said crosslinking agent is divinyl sulfone.
26. A method for producing a microporous, open-celled foam, comprising the steps of:
- (a) mixing hydroxypropyl cellulose (HPC) and water to form a substantially homogeneous, single-phase solution;
 - (b) inducing crosslinking of said HPC by adding a suitable crosslinking agent to said single-phase solution;

- 10 (c) inducing phase separation of said single-phase solution into a polymer-concentrated phase and a polymer-dilute phase after a predetermined period of time, wherein said phase separation is induced by increasing the temperature of said single-phase solution to above the lower consolute solution temperature of said single-phase solution;
- (d) permitting said crosslinking to continue, so that said HPC will crosslink in said concentrated phase for a predetermined period of time during said phase separation to thereby form a microporous material; and
- 15 (e) drying said microporous material to produce said absorbent foam.

27. The method of claim 26, wherein said crosslinking agent is divinyl sulfone (DVS).

28. The method of claim 27, wherein the concentration of HPC is between about 1.9 and about 25 weight percent of said single-phase solution, and wherein the pH of said single-phase solution is above about 11.

29. The method of claim 28, wherein the concentration of DVS is between about 0.2 and about 5.5 weight percent of said single-phase solution.

30. The method of claim 29, wherein said phase separation is induced by increasing the temperature of said solution to above about 40°C.

31. The method of claim 30, wherein said phase separation is induced after said crosslinking has proceeded for between about 1 and about 45 minutes, and said crosslinking is permitted to continue after inducing said phase separation for between about 0.3 and about 100 hours.

32. A method for producing a microporous, open-celled foam, comprising the steps of:

- 5 (a) mixing hydroxyethyl cellulose (HEC), water and a phase-separation enhancer to form a substantially homogeneous, single-phase solution, wherein said phase-separation enhancer is chosen from the group consisting of: a salt, a water-soluble organic solvent, and a combination of a salt and a water-soluble organic solvent;
- 10 (b) inducing crosslinking of said HEC by adding a suitable crosslinking agent to said single-phase solution;
- (c) inducing phase separation of said single-phase solution into a polymer-concentrated phase and a polymer-dilute phase after a predetermined period of time, wherein said phase separation is induced by increasing the temperature of said single-phase solution to above the lower consolute solution temperature of said single-phase solution; and
- 15 (d) - permitting said crosslinking to continue, so that said HEC will crosslink in said concentrated phase for a predetermined period of time during said phase separation to thereby form a microporous material; and
- (e) drying said microporous material to produce said absorbent foam.

33. The method of claim 32, wherein said crosslinking agent is divinyl sulfone (DVS).

34. The method of claim 33, wherein said phase separation enhancer is sodium chloride.

35. The method of claim 33, wherein said phase separation is induced by increasing the temperature of said solution to above about 94°C.

36. The method of claim 35, wherein the pH of said single-phase solution is above about 11, and wherein the concentration of HEC is between about 1.3 and about 18 weight percent of said single-phase solution.

37. The method of claim 36, wherein the concentration of DVS is between about 0.4 and about 2 weight percent.
38. The method of claim 37, wherein said phase separation is induced after said crosslinking has proceeded for between about 1 and about 3 minutes, and said crosslinking is permitted to continue after said inducing for between about 20 and about 60 minutes.
39. A microporous, open-celled foam produced by the method of claim 1.
40. A microporous, open-celled foam produced by the method of claim 26.
41. A microporous, open-celled foam produced by the method of claim 32.
42. An absorbent, microporous foam comprising a crosslinked polymer having interconnected fluid cells distributed throughout its mass, wherein said fluid cells have a diameter of between about 0.1 and about 100 μm , and wherein said foam can rapidly absorb at least about twice its dry weight in fluid.
43. The foam of claim 42, wherein said foam absorbs and retains fluid by a combination of capillary action and pore wall swelling.
44. The foam of claim 42, wherein said foam is superabsorbent, capable of absorbing at least about ten times its dry weight in fluid.
45. The foam of claim 44, wherein said foam has a sorption rate which is at least 100 times faster than a conventionally-made, comparably-sized, non-porous, superabsorbent sheet made from the same polymer as said foam.
46. The foam of claim 44, wherein said foam has approximately the same sorption capacity as a conventionally-made, non-porous, superabsorbent which has been ground and combined with fluff, wherein said conventionally-made superabsorbent has been made from the same polymer as said foam.

47. The foam of claim 44, wherein said does not lose a significant amount of sorption capacity upon repeated drying and resorption of fluid.

48. The foam of claim 47, wherein said polymer is hydrophilic.

49. The foam of claim 48, wherein said polymer exhibits a lower consolute solution temperature (LCST) in an aqueous solution and phase separates from said aqueous solution as the temperature of said solution is increased to above said LCST.

50. The foam of claim 49 wherein said polymer is chosen from the group consisting of: hydrophobically modified carbohydrate polymers, poly(vinyl alcohol-co-vinyl acetate), poly(methacrylic acid), cyanoethylated or partially formalized poly(vinyl alcohol), poly-N-vinyl-2-oxazolidone, polypeptides, acrylate (or analogous methacrylate) copolymers, and
5 N-alkylacrylamide (or analogous N-alkylmethacrylamide) derivatives.

51. The foam of claim 50, wherein said hydrophobically modified carbohydrate polymers include: hydroxypropyl dextran, hydroxypropyl guar, hydroxypropyl starch, hydroxypropyl cellulose (HPC), hydroxyethyl cellulose (HEC), methyl cellulose, hydroxypropylmethyl cellulose, and ethylhydroxyethyl cellulose;
5 wherein said polypeptides include: poly(L-proline), and poly(valine-proline-glycine-X-glycine), wherein X = any amino acid; wherein said acrylate (or analogous methacrylate) copolymers include: hydroxypropyl acrylate-co-acrylamide, diacetone acrylamide-co-hydroxyethyl acrylate, and hydroxypropyl acrylate-co-hydroxyethyl acrylate; and wherein said N-alkylacrylamide (or
10 analogous N-alkylmethacrylamide) derivatives include: ethylacrylamide, cyclopropylacrylamide, n-propylacrylamide, and isopropylacrylamide.

52. The foam of claim 51, wherein said polymer is HPC or HEC.

INTERNATIONAL SEARCH REPORT

I national application No.

PCT/US 95/ 05933

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:

2. ☐ Claims Nos.:
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:

- ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

- 1.- claims 1-5, 7-52: Method for producing a microporous foam where crosslinking is induced AFTER the phase separation.
 - 2.- claim 6: Method for producing a microporous foam where crosslinking is "permitted to proceed for a predetermined period of time PRIOR to said phase separation".
-
1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.

 2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.

 - ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:

 4. ☒ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

1-5, 7-52

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

Inter. Application No.

PCT/US 95/05933

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08J9/28 //A61L15/60, A61F13/15

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP, A, 0 216 622 (GELMAN SCIENCES INC.) 1 April 1987 see claim 1 ---	1-5, 7-52
A	EP, A, 0 365 112 (3M) 25 April 1990 see example 1 see claim 7 ---	1-5, 7-52
A	EP, A, 0 222 718 (NILSSON KJELL G. C.) 20 May 1987 see claim 5 -----	1-5, 7-52



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

A document member of the same patent family

Date of the actual completion of the international search

18 August 1995

Date of mailing of the international search report

07.12.95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

OUDOT, R

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/US 95/05933

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0216622	01-04-87	AU-B- 617613	28-11-91
		AU-B- 5498290	13-09-90
		AU-B- 599599	26-07-90
		AU-B- 6166086	26-03-87
		JP-A- 62116645	28-05-87

EP-A-0365112	25-04-90	US-A- 4863792	05-09-89
		AU-B- 607076	21-02-91
		AU-B- 3669389	26-04-90
		CA-A- 1311885	29-12-92
		DE-D- 68914774	26-05-94
		DE-T- 68914774	20-10-94
		ES-T- 2053994	01-08-94
JP-A- 2129238	17-05-90		

EP-A-0222718	20-05-87	SE-B- 464816	17-06-91
		DE-D- 3689327	05-01-94
		DE-T- 3689327	16-06-94
		JP-A- 62169837	27-07-87
		SE-A- 8504764	16-04-87
		US-A- 5015576	14-05-91
		US-A- 4935365	19-06-90
